

# Technical Data Sheet

03/2023

## *Characteristics*

BLD-GP is one-component, acetic acid type, room temperature curing, high quality silicone glass glue, easy to use, fast curing speed, excellent weather aging resistance, good adhesion to a variety of building materials. Widely used in glass, aluminum alloy, ceramics, glass fiber, non-oil wood and other materials and large-scale engineering bonding and sealing.

BLD-GP    Acid Silicone Sealant				
Performance		Standard	Measured Value	Testing Method
Test at 50±5% RH and temperature 23±2 ℃				
Density (g/cm ³)		±0.1	1.04	GB/T 13477
Tack- Free Time (min)		≤180	10	GB/T 13477
Extrusion (ml/min)		≥80	420	GB/T 13477
Tensile Modulus (Mpa)	23 ℃	≥0.4	0.6	GB/T 13477
Slumpability (mm)vertical		not change shape	not change shape	GB/T 13477
Slumpability (mm)horizontal		≤3	0	GB/T 13477
Curing Speed (mm/d)		2	2.5	GB/T 32369
As Cured - After 21days at 50±5% RH and temperature 23±2 ℃				
Hardness (Shore A)		10~60	28	GB/T531
Tensile Strength under Standard Conditions (Mpa)		/	0.9	GB/T 13477

# Technical Data Sheet

03/2023

Elongation of Rupture (%)	/	260	GB/T 13477
---------------------------	---	-----	------------

## ***Typical Use***

1. Large plate glass bonding sealing;
2. Bonding and sealing of point glass engineering;
3. Installation of all kinds of aluminum alloy, stainless steel and other doors and windows;
4. Bonding and sealing of daylighting glass shed.

## ***Direction for use***

1. Rinse the surface where you will stick with acetone or other solvent;
2. Paste the low viscosity adhesive tape on the place that needs protection; Recondition and remove the adhesive tape before the sealant becomes solidifying;
3. Product applicability should be confirmed in user's sole judgement. Please do the compatibility test before official use to make sure that it can stick well with the substrate materials and full the interface, otherwise we are not responsible for any complaints of application.

## ***Safety Rules***

1. Keep the work field drafty.
2. In case of contact with eyes, rinse with plenty of water and appeal to the doctor immediately.
3. Keep away from the children.

## ***Limitation***

1. Should not use as structural sealant.
2. Should not be used on the oily or oil-leaking, frosty or damp surface and in the airtight places, nor the material surface which the temperature is below 4 °C or above 40 °C.

## ***Storage***

1. Should be stored separately in cool and dry places, temperature below 27 °C.
2. 12 months shelf life since the date of production.

## ***Transportation***

Transported as unhazardous goods.

## ***Color***

Transparent, black, white and grey, and colors for customers' needs.