

Technical Data Sheet

06/2019

Characteristics

BLD-8809 is a two-component, neutral-curing, high-modulus silicone sealant.

Product Features

- Excellent extrusion from low temperature (+5°C) to high temperature (+40°C)
- Good flexibility from low temperature (-40°C) to high temperature (+150°C)
- Long storage period
- Low curing shrinkage
- Fast curing: short de-stick time
- Excellent adhesion to glass and aluminum.

Data Sheet

1. Uncured product characteristics

Appearance	Homogeneous and delicate paste
Odor	Alcoholic
Color	White, black
Fluidity after mixing	0
Specific gravity at 25°C	1.50g/ml
Extrusion rate, g/min	240

2. When curing

After mixing the A and B components of BLD6609 at a volume ratio of A:B=10:1, the whole begins to thicken and solidify. The curing rate increases with increasing temperature and humidity.

Applicable period, min	60
Density after curing, g/ml	1.4
23°C, 50% RH, surface drying time, min	60-90

3. Product performance after curing

Shore hardness A	46
100 % modulus of elasticity, MPa	0.9
Tensile strength, MPa	1.2
Elongation at break, %	200

Technical Data Sheet

06/2019

4. Thermal properties (2mm film thickness) ¹

Lower limit of service temperature	-50°C
Upper temperature limit for continuous use	+150°C (maximum temperature at 1000h)
Maximum instantaneous operating temperature	+185°C (Maximum temperature at 72h)

5. Adhesive properties

After curing at 23°C x 50% RH for 14 days, refer to standard GB/T13477.18-2002, 2mm specimen thickness on the surface of the substrate is stretched in 180° direction and the percentage of peel strength and cohesive damage area is recorded.

Glass, MPa	1.2
AG3 Aluminum, MPa	1.2
Stainless steel/glass, MPa	1.2
Type of damage	100% cohesive damage

Areas of application

- For the structural assembly of glass curtain walls
- Particularly suitable for the structural bonding of glass and metal elements of curtain wall units in workshop assemblies and for the structural bonding of insulating glass assemblies.

Direction for use

- Clean the surface of the material to be bonded with acetone or other solvent and keep it dry before application.
- Ensure that the sealant is in close contact with the substrate and that there are no gaps in the adhesive.
- Apply low viscosity tape to the area to be protected, trim and remove the tape before the adhesive has cured.

Restrictions on use

- Not suitable for use on oily or oozing surfaces, frosty or wet surfaces and should not be applied to surfaces where the temperature of the material is below 4°C or above 40°C.
- Not suitable for use in densely ventilated areas (silicone sealants need to be cured by absorbing moisture from the air)
- Not suitable for use in areas subject to abrasion or physical damage.

¹ Based on mechanical properties and Shore A hardness before and after testing for heat ageing. These operating temperatures are not absolute limits, they represent the temperature range at which the

mechanical properties are reduced to more than 50% of their initial value. Higher temperatures can be tolerated instantaneously, if not continuously for 72 hours.

Technical Data Sheet

06/2019

-
- Not suitable for use in areas where there is direct contact with food surfaces

¹ Based on mechanical properties and Shore A hardness before and after testing for heat ageing. These operating temperatures are not absolute limits, they represent the temperature range at which the mechanical properties are reduced to more than 50% of their initial value. Higher temperatures can be tolerated instantaneously, if not continuously for 72 hours.

Technical Data Sheet

06/2019

Cautions

- Before using the product, the user must carry out compatibility and adhesion tests to confirm that the product and the substrate can meet the requirements of the application.
- The product should be designed correctly according to the actual force of the interface, so that the sealant has the proper effect and meets the displacement capacity of the interface.
- The width of the butt joint should be not less than 6mm but not more than 15mm and the thickness of the adhesive layer should be not less than 3mm but not more than 5mm.
- In case of contact with eyes, rinse immediately with plenty of water and seek medical advice; avoid contact with children

Storage

The silicone sealant should be stored in a cool, dry place below 27°C. The storage period is 9 months from the date of manufacture.

Transport

This product is to be transported as non-dangerous goods.

Colors

Black, white.

Packaging specifications

Component A in 190L drums; Component B in 19L drums.

NO.008, YINGLONG ROAD, LONGSHANHIGH TECHINDUSTRIAL PARK,
LINQU COUNTY, SHANDONG PROVINCE,
CHINA Tel.: 86-536-3350888

Website: <http://www.cnblld.com.cn>

Email: silicone@junyuannewmaterial.com